



Item	Unit	Value
thickness	μm	25-700
Dyne value	min	34
Tensile Strength	Psi	6000
Elongation to break rate	%	70-100
cold fracture temperature	°F	-4
proportion	g/cm ³	1.4
Vicat softening temperature	°C	89
luster	°	60

Zhejiang Kaixin Optoelectronics Technology Co., Ltd.

No. 2288, Xiaoyue Street, Shangyu District, Shaoxing City, Zhejiang Province, 312000, China

Email: sales@kaixinfilm.com

Website: <https://www.kaixinfilm.com>