



Item	Unit	Value
thickness	μm	25-700
Tensile Strength	Psi	5800
Flexural modulus	Psi	9000
Bending strength	Psi	2.9-3.8*100000
Heat distortion temperature	degrees celsius	150
proportion	g/cm ³	1.4
Vicat softening temperature	°C	78
Rockwell hardness	R	110

Zhejiang Kaixin Optoelectronics Technology Co., Ltd.

No. 2288, Xiaoyue Street, Shangyu District, Shaoxing City, Zhejiang Province, 312000, China

Email: sales@kaixinfilm.com

Website: <https://www.kaixinfilm.com>